

ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

# Datasheet AE250HVF



AE250HVF is a high impact Nylon which maintained even at low temperatures. Is particularly suitable for recoil-free hammer heads.

### Application

Particularly suitable for recoil-free hammer heads

# Material

Polyamide 6.6 High Impact.

#### Availablity

	Value	Unit
Rod diameters	10-100	mm
Tube inside diameter	on request	
Tube outside diameter	on request	
Length standard	on request	
Sheet thickness	on request	
Sheet size	on request	

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.



ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

# **AE250HVF - Specifications**

### **Physical properties**

	Test standard	Value	Unit
Density		1,09	g/cm³
Thermal conductivity		on request	
Specific heat capacity		on request	
Moisture absorption at 23°C, 50% RH	ISO 62	2,2	%
Water absorption at 23 °C	ISO 62	7	%
Flammability		on request	

#### **Mechanical properties**

	Test standard	Value	Unit
Hardness	ISO 868	80	SHORE-D
Yield stress	ISO 527	60	MPa
Elongation at break	ISO 527	32	%
Modulus of elasticity in tension	ISO 527	2000	MPa
Bending modulus	Flexural test	2300	MPa
Flexural strength	ISO 178	110	MPa
Charpy impact strength +23°C	ISO 179/1eU	no break	kJ/m²
Charpy notched impact strength +23°C	ISO/1eA	80	kJ/m²
Ball indentation hardness	ISO 2039-1	165	N/mm²
Compressive modulus	ISO 604	2800	MPa

#### **Thermal properties**

	Test standard	Value	Unit
Min. working temperature		-30	°C
Max. working temperature		90	°C
Intermittent working temperature		160	°C
Heat distortion temperature	Method A ISO 75	70	°C
Melting temperature	ISO 3146	263	°C
Glass transition temperature	ISO 3146	60	°C
Thermal coefficient of linear expansion	DIN 53752	10	1/K.10-5

#### **Friction properties**

Test standard	Value	Unit

# **Electrical properties**

	Test standard	Value	Unit
Dielectric constant		on request	
Dielectric loss factor		on request	
Dielectric strength	IEC 243	27	KV/mm
Dielectric constant at 1MHZ	IEC 250	2,9	[-]

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.

ASEC Products 2022 ©.

# **Electrical properties**

Volume resistivity	IEC 93	10 14	Ω.cm
Surface resistivity	IEC 93	10 14	Ω
Resistance to tracking (CTI)	DIN EN 60112	600	[-]
Dissipation factor 1 MHz	IEC 250	0,03	[-]

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.