

ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

Datasheet AIEPCP201



AI EP CP 201 is a composite with paper as a base, strengethened with epoxy

Application

Material

Epoxy strengethened paper -based composite

Availablity

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	



The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.



ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

AIEPCP201 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,35	g/cm³
Water absorption at 23 °C		on request	
Flammability		on request	

Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		80	MPa
Shear strength		on request	
Impact strength		on request	
Flexural strength		110	MPa
Insulation resistance		on request	
Elastic modulus from bending test		6.000	MPa
Compressive strenth perpendicular		160	MPa
Izod impact strength, parallel with layers		on request	
Shear strength parallel		on request	

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		110	т.і.

Friction properties

Test standard	Value	Unit

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		13	kV/mm
Resistance to tracking (CTI)		100	СТІ
Permittivity 50Hz		5	[-]
Permittivity 1MHz		5	[-]
Dissipation factor 50Hz		0,05	[-]
Dissipation factor 1 MHz		0,05	[-]
Insulation resistance after submersion in water		10.000	ΜΩ

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.