ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

Datasheet AIEPGC203



AI EP GC 203 Has high mechanical strength at elevated temperatures. Particularly good stability of electrical properties under high humidity. Mechanical, electrical, and electronic applications. Can be used at cryogenic temperatures. Incredibly good resistance to chemicals.

Application

For use in mechanical, electrical and electronic applications.

Material

Epoxy with woven glass cloth composite.

Availablity

	Value	Unit
Sheet thickness	0,15-150	mm
Sheet size	1250x1250/2500	mm





The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

AIEPGC203 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,85	g/cm³
Water absorption at 23 °C	ISO 62-1	15	mg
Flammability		on request	

Mechanical properties

	Test standard	Value	Unit
Compressive strength static	ISO 604	550	MPa
Module of elasticity - Youngs modulus	ISO 178	22000	MPa
Tensile strength	ISO 527	320	MPa
Shear strength		on request	
Impact strength		on request	
Bending strenght	ISO 178	450	MPa
Flexural strength		on request	
Insulation resistance		on request	
Elastic modulus from bending test		on request	
Compressive strenth perpendicular		on request	
Izod impact strength, parallel with layers	ISO 180/2A	65	kJ/m²
Shear strength parallel	ISO 60893-2	50	MPa

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)	IEC 60216	160	ºC

Friction properties

	Test standard	Value	Unit

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		on request	
Resistance to tracking (CTI)	IEC 60112	200	CTI
Permittivity 50Hz	IEC 60250	4,5	[-]
Permittivity 1MHz	IEC 60250	4,5	[-]
Dissipation factor 50Hz	IEC 60250	0,008	[-]
Dissipation factor 1 MHz	IEC 60250	0,01	[-]
Insulation resistance after submersion in water	ISO 60167	500	MΩ

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.