

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

# **Datasheet AlHydropanel**



ASHydropanel is a multifunctional all-round fiber cement board with excellent properties in terms of impact resistance, fire resistance, sound insulation and moisture resistance. This board is stronger and harder than plasterboard because it is made of Portland cement, mineral fillers (e.g., mica), organic reinforcement fibers and additives. A ASHydropanel board is autoclaved, sanded and sawn square. This board has many advantages. It is not inflammable and does not spread fire (fire reaction class A2-s1, d0 according to NEN EN13501-1). It is not only resistant to many living organisms (fungi, bacteria, insects, vermin, etc.) but also to various temperatures. Furthermore, it is airtight and vapor permeable and has a high impact resistance. It ensures high dimensional stability and low hygroscopic movement thanks to the selected mineral fillers.

#### **Application**

Interior wall: Non-load-bearing partition wall, pre-wall, wood frame wall, steel frame wall. Interior floor: finishing support plate on load-bearing floors and floating floors Interior ceiling: suspended ceilings, swimming pool ceilings

#### **Material**

Fibre cement board

#### **Availablity**

	Value	Unit
Sheet thickness	6, 9, 12	mm
Sheet size	600/900/1200/1250x1200/2500/2600/3000	mm



ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

# **AlHydropanel - Specifications**

#### **Physical properties**

	Test standard	Value	Unit	
Density	EN 12467	1,18	g/cm³	
Thermal conductivity		on request		
Specific heat capacity	at 23°C	1018	I/a.K	

#### **Mechanical properties**

	Test standard	Value	Unit
Module of elasticity - Youngs modulus	Airdry	10	N/mm²
Flexural strength	airdry	23	N/mm²

### Thermal properties

	37-1	
Test standard	Value	lUnit
		•

# **Friction properties**

Test standard	Value	Unit
---------------	-------	------

# **Electrical properties**

Test standard Value		Test standard	Value	Unit
---------------------	--	---------------	-------	------

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.