

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

Datasheet AIMFGC21



AI MF GC 201 Is suitable for mechanical and electrical applications. Arc-resistant and tracking-resistant material. Good flame resistance. Self-extinguishing. Halogen-free. Lower high-voltage values and insulation resistance than other AI EP GC and AI PF GC.

Application

Mechanical and electrical applications.

Material

Melamine strengethened cotton cloth- based composite

Availablity

_		
	Value	Unit
Rod diameters	on request	
Tube inside diameter	on request	
Tube outside diameter	on request	
Length standard	on request	





The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.



ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

AIMFGC21 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,8	g/cm³
Water absorption at 23 °C	ISO 62-1	1	mg/cm²
Flammability		on request	

Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		on request	
Shear strength		on request	
Impact strength		3,3	Charpy or Izod
Bending strenght	ISO 178	300	MPa
Flexural strength		on request	
Insulation resistance		0,01	$M\Omega$
Elastic modulus from bending test		80	MPa
Compressive strenth perpendicular		150	MPa

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)	IEC 60216	130	ōC.

Friction properties

		Test standard	Value	Unit
--	--	---------------	-------	------

Electrical properties

	Test standard	Value	Unit
Dielectric strength parallel		10	kV
Permittivity 50Hz	IEC 60250	6	[-]
Permittivity 1MHz	IEC 60250	6	[-]
Dissipation factor 50Hz	IEC 60250	0,02	[-]
Dissipation factor 1 MHz	IEC 60250	0,01	[-]
Insulation resistance after submersion in water	IEC 60167	100	ΜΩ

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.