

ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

Datasheet AIPFCP205



Al PF CP 205 is a phenolic strengethened paper based composite material

Application

Material

Phenolic strengethened paper based composite

Availablity

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	



The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.



ASEC Products Marketing 17 6921 RE Duiven The Netherlands T. +31 316 84 44 01 info@asecproducts.com www.asecproducts.com

AIPFCP205 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,35	g/cm³
Water absorption at 23 °C		113	mg
Flammability		V-1	[-]

Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		60	MPa
Shear strength		20	Мра
Impact strength		on request	
Flexural strength		75	MPa
Insulation resistance		on request	
Elastic modulus from bending test		5.000	MPa
Compressive strenth perpendicular		250	MPa
Izod impact strength, parallel with layers		on request	
Shear strength parallel		on request	

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		100	т.і.

Friction properties

Test standard	Value	Unit

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		8,4	kV/mm
Resistance to tracking (CTI)		100	СТІ
Permittivity 50Hz		on request	
Permittivity 1MHz		5,5	[-]
Dissipation factor 50Hz		on request	
Dissipation factor 1 MHz		0,05	[-]
Insulation resistance after submersion in water		1.000	ΜΩ

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet. ASEC Products 2022 ©.