

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

Datasheet AIPFCP207



Al PF CP 207 is a phenolic strengethened paper based composite material

Application

Material

Phenolic strengethened paper based composite

Availablity

	Value	Unit
Sheet thickness	on request	
Sheet size	on request	





The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.



ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

AIPFCP207 - Specifications

Physical properties

	Test standard	Value	Unit
Density	ISO 1183-A	1,35	g/cm³
Water absorption at 23 °C		920	mg
Flammability		on request	

Mechanical properties

Treetiament properties			
	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		100	MPa
Shear strength		10	Мра
Impact strength		on request	
Flexural strength		80	MPa
Insulation resistance		on request	
Elastic modulus from bending test		5.000	MPa
Compressive strenth perpendicular		300	MPa
Izod impact strength, parallel with layers		on request	
Shear strength parallel		on request	

Thermal properties

	Test standard	Value	Unit
Thermal endurance 20,000 h (T.I)		105	T.I.

Friction properties

Test standard	Value	Unit
---------------	-------	------

Electrical properties

	Test standard	Value	Unit
Dielectric strength perpendic thickness 3 mm		on request	
Resistance to tracking (CTI)		100	CTI
Permittivity 50Hz		on request	
Permittivity 1MHz		on request	
Dissipation factor 50Hz		on request	
Dissipation factor 1 MHz		on request	
Insulation resistance after submersion in water		on request	

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.