
ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

Datasheet ASSPFW



ASEC SP spherical plain bearings are well suited for all rotating pivot points, in particular for oscillating movements, where the shaft must be self-aligning. Spherical plain bearings are for example particularly recommended for the eyes of hydraulic cylinders. As cylinders are always oscillating, they must be able to move freely without any sideload on the rod at any time during the movement. A sideload causes an axial load on the guide and seals of the piston rod, which can lead to leakages. The parallel movement of the cylinder and the spherical plain bearing prevent such leakage.

Application

High end sperical slide bearing - Stailes steel spherical ball - Interchangeable with other types - Sizes according ISO 12240 - High load and shock resistant - Enviromental friendly - Suitable for dry running - Low friction material - Suitable for edge loading - High wear resistance

Material

Complete composite inner and outer ring.

Availablity

	Value	Unit
Tube inside diameter	15-400	mm
Tube outside diameter	26-550	mm
Length standard	12-230	mm



The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.

ASEC Products
Marketing 17
6921 RE Duiven
The Netherlands
T. +31 316 84 44 01
info@asecproducts.com
www.asecproducts.com

ASSPFW - Specifications

Physical properties

	Test standard	Value	Unit
Density		Not applicable	
Max. swell in water at 20 °C	ASTM D570	<0,1	%

Mechanical properties

	Test standard	Value	Unit

Thermal properties

	Test standard	Value	Unit
Min. working temperature		-196	°C
Max. working temperature		120	°C
Intermittent working temperature		140	°C

Friction properties

	Test standard	Value	Unit
Coefficient of friction dynamic	pin-on-ring/dry against steel	0,05-0,22	[-]
Max. sliding speed		2,0	m/s
Max. Pv-load dry	pin-on-ring	0,25	MPa*m/s
Max. Pv-load oil lubricated	pin-on-ring	0,5	MPa*m/s
Max. Pv-load on regular greased	pin-on-ring	2	MPa*m/s

Electrical properties

	Test standard	Value	Unit

The information in this datasheet is provided for general purposes only and not meant to be a specific recommendation for any individual application. All values were determined under laboratory conditions. ASEC Products is not directly neither indirectly responsible for any claim resulting from the use of any information provided in this datasheet.
ASEC Products 2022 ©.