

## Datasheet TEBRM95



TEBRM95 is based on bronze and embedded with solid lubricants. Because it is made of bronze, which performs well in terms of elongation, it can be processed into a wrapped bushing with thin wall thickness. In addition, the embedded lubricant is ideal for lubrication, and the bushing can be used in car transmission shafts and other circumstances without oil lubrication.

### Application

Suits for oil free lubrication

### Material

Bronze with graphite.

### Availability

	Value	Unit
Inside diameter	on request	
Outside diameter	on request	
Flange diameter	on request	
Flange height	on request	
Total length	on request	

## TEBRM95 - Specifications

### Physical properties

	Test standard	Value	Unit
Thermal conductivity		60	CW0/m.k.

### Mechanical properties

	Test standard	Value	Unit
Compressive strength static		on request	
Module of elasticity - Youngs modulus		on request	
Tensile strength		450	Mpa
Shear strength		on request	
Impact strength		on request	
Hardness		70-100	Rockwell HB
Dynamic load capacity		65	MPa

### Thermal properties

	Test standard	Value	Unit
Min. working temperature		-100	°C
Max. working temperature		260	°C
Intermittent working temperature		on request	

### Friction properties

	Test standard	Value	Unit
Coefficient of friction dynamic		0.06-0.2	[-]
Max. sliding speed		4	m/s
Max. Pv-load dry		2,6	MPa*m/s
Max. Pv-load oil lubricated		15	MPa*m/s
Max. Pv-load on regular greased		on request	

### Electrical properties

	Test standard	Value	Unit
--	---------------	-------	------